

**PRODUCT:** EVERGLASS® Short Strand Fiber Reinforced Filler

**PART NUMBER:** 100632      **Quart**      **6 units/case**  
100622      **Gallon**      **4 units/case**

**DESCRIPTION:** EVERGLASS® is a short strand multi-fiber reinforced body repair filler ideal for use on metal for finishing welded seams, rusted metal repairs, and repairing composites for filling holes in SMC/Fiberglass, and shattered fiberglass.

**APPROVED SUBSTRATES:**




- Steel
- Galvanized Steel
- Aluminum
- SMC
- Fiberglass
- Most Rigid Plastics

**PREPARATION:**



- Clean and degrease the entire panel to be repaired with soap and water, followed by a mild cleaning solvent. Surface must be thoroughly dry before repairing or applying material.
- Keep the repair area small. Use 40-80 grit to remove the paint and featheredge.

**MIXING:**



- Stir the filler before using. Knead the cream hardener.
- Measure hardener 2% by weight (add a ribbon of cream hardener from edge to edge across the center of a 4" diameter puddle).
- Puddles larger than 4" (10 cm) in diameter will require additional hardener. Mix thoroughly until uniform color is achieved.
- Approximate setting time is 5-6 minutes @ 72°F-80°F (22°C)

**APPLICATION:**



- Apply in layers with even firm pressure.
- Do not apply all at once.

### FINISH:



- Sand filler with 80 grit sandpaper.
- If necessary, reapply additional coats, or apply a finish coat of any Evercoat lightweight filler or polyester putty.

### TECHNICAL SPECIFICATIONS:

- |                                      |   |
|--------------------------------------|---|
| ▪ Appearance                         | Dk. Green Fibrous Paste                     |
| ▪ VOC                                | Refer to Section 9 of the Safety Data Sheet |
| ▪ Relative Density                   | Refer to Section 9 of the Safety Data Sheet |
| ▪ Sand Time                          | 10-15 min.                                  |
| ▪ Max Recommended Thickness (sanded) | 1/4 inch (6mm)                              |

**NOTE:** Properties are typical values and should not be considered as sales specifications. Physical testing performed @ ~72°F (22°C) / 75% RH unless otherwise noted.

### SAFETY & HANDLING:

Read all directions and warnings prior to using Evercoat® products. Safety Data Sheets can be found online at [evercoat.com](http://evercoat.com).

### NOTES:

Never return mixed filler to can

Keep can closed and store in a cool dry place

***USE WITH CREAM HARDENER ONLY!***